

General Information

Description

- ◆ MF5000 is manufactured to be processed in flat yarn for tarpaulin by CSTR Slurry process technology.
- ◆ MF5000 is ideally suited for use in monofilament application.
- ◆ MF5000 offers good stretching, spinning, high strength property and melting stability.

Additives

- ◆ Antioxidant

Applications

- ◆ Monofilament for Rope and Net, etc.

Physical Properties¹

Properties	Test Method	Nominal Value	
Melt Index, at 190 °C/2.16kg	ASTM D 1238	0.95	g/10min
Density	ASTM D 1505	0.954	g/cm ³
Tensile Strength at Break	ASTM D 638	320	kg/cm ² 31.4 MPa
Elongation at Break	ASTM D 638	> 500	%
Flexural Modulus	ASTM D 790	10,000	kg/cm ²
Rockwell Hardness	ASTM D 785	50	R
IZOD Impact Strength, at 23 °C	ASTM D 256	20	kg·cm/cm
VICAT Softening Point	ASTM D 1525	124	°C
Heat Distortion Temp	ASTM D 648	74	°C

Note

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com