

March, 2017

HOPELEN J-150

PP HOMOPOLYMER

General Information

Description

J-150 is homo polymer resin produced through the polymerization of propylene. This grade is designed to be processed in conventional Injection molding equipment. J-150 shows good thermal stability and has high strength and stiffness. It is typically used in production of housewares and the general supplies.

Applications

Housewares and general supplies

| Physical Properties ¹ | | | | | | |
|------------------------------------------|-------------|--------|---------------------|-------|-----|--|
| Physical | Test Method | | Nominal Values | | | |
| Melt Flow Index | ASTM D1238 | 10 | g/10min | | | |
| Density | ASTM D792 | 0.90 | g/cm ³ | | | |
| Mechanical | | | | | | |
| Tensile Stress (Yield) | ASTM D638 | 370 | kgf/cm ² | 36 | MPa | |
| Tensile Strain (Break) | ASTM D638 | >100 | % | >100 | % | |
| Flexural Modulus | ASTM D790 | 17,000 | kgf/cm ² | 1,670 | MPa | |
| Impact | | | | | | |
| Notched Izod Impact Strength (23℃) | ASTM D256 | 3.0 | kgf-cm/cm | 29 | J/m | |
| Notched Izod Impact Strength (-10℃) | ASTM D256 | 2.5 | kgf-cm/cm | 25 | J/m | |
| Thermal | | | | | | |
| Heat Deflection Temperature (4.6kgf/cm²) | ASTM D648 | 120 | ${\mathbb C}$ | | | |
| Additional Properties | | | | | | |
| Flammability | UL94 | НВ | | | | |

| NOTE | ISO 9001, 14001, /TS 16949 | | | | | |
|-------------------------------------------------------------------------|----------------------------|--|--|--|--|--|
| 1 Physical Proporties : these are not to be construed as specifications | | | | | | |

www.lottechem.com



March, 2017

HOPELEN J-150

PP HOMOPOLYMER

General Information

Description

J-150 is homo polymer resin produced through the polymerization of propylene. This grade is designed to be processed in conventional Injection molding equipment. J-150 shows good thermal stability and has high strength and stiffness. It is typically used in production of housewares and the general supplies.

Applications

Housewares and general supplies

| Physical Properties ¹ | | | | | | |
|------------------------------------------|-------------|--------|---------------------|-------|-----|--|
| Physical | Test Method | | Nominal Values | | | |
| Melt Flow Index | ISO 1133 | 10 | g/10min | | | |
| Density | ISO 1183 | 0.90 | g/cm ³ | | | |
| Mechanical | | | | | | |
| Tensile Stress (Yield) | ISO 527-1 | 350 | kgf/cm ² | 34 | MPa | |
| Tensile Strain (Break) | ISO 527-1 | >100 | % | >100 | % | |
| Flexural Modulus | ISO 178 | 13,500 | kgf/cm ² | 1,320 | MPa | |
| Impact | | | | | | |
| Notched Izod Impact Strength (23℃) | ISO 180 | 2.5 | kgf·cm/cm | 25 | J/m | |
| Notched Izod Impact Strength (-10℃) | ISO 180 | 2.0 | kgf·cm/cm | 20 | J/m | |
| Thermal | | | | | | |
| Heat Deflection Temperature (4.6kgf/cm²) | ISO 75-1 | 100 | C | | | |
| Additional Properties | | | | | | |
| Flammability | UL94 | НВ | | | | |

| NOTE | ISO 9001, 14001, /TS 16949 |
|-------------------------------------------------------------------------|----------------------------|
| 1 Physical Proporties : these are not to be construed as specifications | |

www.lottechem.com